



ANTI-SLIP SOLUTIONS

mail@heskins.com

www.heskins.com

24/04/2024

H3447 Chemical Resistant Safety-Grip™ Data Sheet

Subject	Result	Test Method
Base film	0.1mm PVC	Caliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel (g/25.4mm ²)	1500↑	PSTC-4
Tensile strength (kg/25.4mm ²)	6.0↑	PSTC-31
Tear resistance (g)	5600 +/- 200	PSTC-39
Elongation at break	25%↑	PSTC-31
Temperature range	-30°C to +70°C	See notes below
Maximum size of production roll	1168mmx100m	N/A
Resistance to motor oil	Excellent	PSTC-35

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H3447N (Black)	9004	Black U	0	0

Coefficient of Friction Data

Safety-Grip™	Dry Surface Test Result	Wet Surface Test Result
Chemical Resistant	102 TRL	71 TRL

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins Ltd 1997-2024

