

Heskins hazard photoluminescent safety-grip data sheet

Subject	Result	Test method
Back carrier	0.003" PVC	Caliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel	1500↑	PSTC-4
(oz/l"²)		
Tensile strength	6.0↑	PSTC-31
(lb./l ^{**2})		
Tear resistance (oz)	5600 +/- 200	PSTC-39
Elongation at break	25%↑	PSTC-31
Temperature range	-22F to 158F	See notes below
Maximum size of	46"x328ft	N/A
production roll		
Resistance to water	10	PSTC-35
(months)		
Resistance to chemicals	8	PSTC-35
(months)		
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

Glow in the dark safety-grip® results

30 millicandela per m² at 2 minutes, 5mcd after 10 minutes

Coefficient of friction data

Safety-Grip®	Dry surface test result	Wet surface test result
Standard	I02 TRL	71 TRL

All the above data is for reference only.

©Heskins LLC 2016
